

03-24-03

A

Atty. Docket No. KIK01 P-319

CERTIFICATE OF MAILING BY EXPRESS MAIL

I hereby certify that this paper, together with all enclosures identified herein, are being deposited with the United States Postal Service as Express Mail, using label No. EL545347385US, addressed to the Assistant Commissioner for Patents, Box Patent Application, Washington D.C. 20231, on the date indicated below.

March 23, 2000

Date

Deborah A. Witvoet
Deborah A. Witvoet

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant : Kimihiro Yamashita

For : METHOD FOR CONTROLLING ORGANISMS AND MATERIAL THEREFOR, METHOD FOR SELECTIVE ADSORPTION OF PROTEINS AND MATERIAL THEREFOR, CEMENT MATERIAL AND BIOMATERIAL

Assistant Commissioner for Patents
Box Patent Application
Washington, D.C. 20231

Dear Sir:

Enclosed herewith is the above-identified patent application comprising the following parts:

- 1) Postcard
- 2) 22 Pages of Specification
- 3) 4 Pages of Claims (16 claims)
- 4) 1 Page of Abstract
- 5) Preliminary Amendment (5 new claims)
- 6) 16 Sheets of Drawings (in duplicate)
- 6) Declaration and Power of Attorney (unexecuted)
- 7) Verified Statement Claiming Small Entity Status
(37 CFR §1.9[f] and 1.27[c]) – Small Business Concern (unexecuted)
- 8) Claim of Priority, along with a certified copy of Japanese Patent Application Serial No. 11-77089, filed March 23, 1999 and Japanese Patent Application Serial No. 2000-3545, filed January 12, 2000

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant : Kimihiro Yamashita

For : METHOD FOR CONTROLLING ORGANISMS AND MATERIAL
THEREFOR, METHOD FOR SELECTIVE ADSORPTION OF
PROTEINS AND MATERIAL THEREFOR, CEMENT MATERIAL
AND BIOMATERIAL

BOX PATENT APPLICATION
Assistant Commissioner for Patents
Washington, D.C. 20231

Dear Sir:

PRELIMINARY AMENDMENT

Please amend the above-referenced application as follows.

In the Claims:

1. Amend claim 3, line 1, by deleting the words "any of claims 1 and 2" and inserting therefor the words - -claim 1- -.
2. Amend claim 6, lines 1 and 2, by deleting the words "any of claims 4 and 5" and inserting therefor the words - -claim 4- -.
3. Amend claim 10, lines 1 and 2, by deleting the words "any of claims 8 and 9" and inserting therefor the words - -claim 8- -.
4. Amend claim 13, line 1, by deleting the words "any of claims 11 and 12" and inserting therefor the words - -claim 11- -.
5. Amend claim 16, line 1, by deleting the words "any of claims 14 and 15" and inserting therefor the words - -claim 14- -.

Applicant : Kimihiro Yamashita
For : METHOD FOR CONTROLLING ORGANISMS AND MATERIAL
THEREFOR, METHOD FOR SELECTIVE ADSORPTION OF
PROTEINS AND MATERIAL THEREFOR, CEMENT MATERIAL
AND BIOMATERIAL
Page : 2

Please add the following claims:

17. A method for controlling organisms according to claim 2, wherein the ceramic is powder, fiber or a coating film.

18. A material for controlling organisms according to claim 5, wherein the ceramic is powder, fiber or a coating film.

19. A material for controlling organisms according to claim 9, wherein the ceramic is powder, fiber or a coating film.

20. A cement material according to claim 12, wherein the ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are materials selected from hydroxyapatite ceramics, barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially stabilized zirconia ceramics; ion conductive alumina ceramics; and piezoelectric ceramics containing lead.

21. A biomaterial according to claim 15, wherein the ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are materials selected from hydroxyapatite ceramics, barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially stabilized zirconia ceramics; ion conductive alumina ceramics; and piezoelectric ceramics containing lead.

Applicant : Kimihiro Yamashita
For : METHOD FOR CONTROLLING ORGANISMS AND MATERIAL
THEREFOR, METHOD FOR SELECTIVE ADSORPTION OF
PROTEINS AND MATERIAL THEREFOR, CEMENT MATERIAL
AND BIOMATERIAL
Page : 3

REMARKS

The above-referenced application has been amended to remove all multiple dependent claims, and thereby reduce the filing fee.

Respectfully submitted,

KIMIHIRO YAMASHITA

By: Price, Heneveld, Cooper,
DeWitt & Litton

March 23, 2000

Date



Gunther J. Evahina

Registration No. 35 502

695 Kenmoor, S.E.

Post Office Box 2567

Grand Rapids, Michigan 49501

(616) 949-9610

GJE/daw

ABSTRACT OF THE DISCLOSURE

A method for controlling organisms which comprises growing, decreasing, activating or inactivating cells, bacteria, viruses or fungi at an N-surface or a P-surface of a ceramic which is formed by treating the ceramic by polarization; and a material for controlling organisms, a method for selective adsorption of proteins, a material for selective adsorption of proteins, a cement material for filling bones and dental applications and a biomaterial, in which the ceramic treated by polarization is utilized.

By utilizing difference in properties among surfaces of the ceramic treated by polarization, growth, decrease, activation or inactivation of organisms such as cells, bacteria, viruses or fungi can be controlled. Therefore, the above methods and materials are useful in the medical, dental and biochemical areas.

METHOD FOR CONTROLLING ORGANISMS AND MATERIAL
THEREFOR, METHOD FOR SELECTIVE ADSORPTION OF PROTEINS
AND MATERIAL THEREFOR, CEMENT MATERIAL AND
BIOMATERIAL

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a ceramic (including powder and fiber) treated by polarization and, more particularly, to a method for growing, decreasing, activating or inactivating cells, bacteria or the like and a material therefor, in which a ceramic treated by polarization is utilized.

The present invention also relates to a method for selective adsorption of proteins by utilizing difference in the absorption properties among surfaces of a ceramic which are formed by treating the ceramic by polarization and a material therefor.

The present invention further relates to a cement material for filling bones and dental applications which comprises powder of a ceramic treated by polarization.

2. Description of Related Art

It has been proposed by the present inventors in Japanese Patent Application Laid-Open No. Heisei 10(1998)-324584 that a ceramic, an inorganic material, having affinity to biomaterials which is obtained by treating a ceramic by polarization can be used as a tooth material to reinforce or replace a tooth bone and increases the growth rate of crystals similar to bone materials.

SUMMARY OF THE INVENTION

An object of the present invention is to provide a method for controlling organisms, i.e., growing, decreasing, activating and inactivating cells and tissues of organisms, which can be applied to a wide range of areas such as the medical, dental and biochemical areas and to antibiotic applications and a material therefor, a method for selective adsorption of proteins and a material therefor and a cement material for filling bones and dental applications.

The present invention provides:

- (1) A method for controlling organisms which comprises growing, decreasing, activating or inactivating cells, bacteria, viruses or fungi at an N-surface or a P-surface of a ceramic which is formed by treating the ceramic by polarization;
- (2) A material for controlling organisms which is a ceramic treated by polarization so that cells, bacteria, viruses or fungi are grown, decreased, activated or inactivated at an N-surface or a P-surfaces of the ceramic which is formed by the treatment;
- (3) A method for selective adsorption of proteins which comprises selectively adsorbing drugs, nutrients and proteins by utilizing difference in adsorption properties among an N-surface, an O-surface and a P-surface of a ceramic which are formed by treating the ceramic by polarization;
- (4) A material for selective adsorption of proteins which is a ceramic treated by polarization so that drugs, nutrients and proteins are selectively adsorbed due to difference in adsorption properties among an N-surface, an O-surface and a P-surface of a ceramic which are formed by

treating the ceramic;

(5) A cement material for filling bones and dental applications which comprises powder or fiber of a ceramic treated by polarization;

(6) A biomaterial which is obtained by treating a ceramic having affinity to biomaterials by polarization in an atmosphere of steam at a temperature from a room temperature to 1,000°C; and

(7) A biomaterial which is obtained by treating a ceramic having affinity to biomaterials by polarization at a voltage from 10 to 100,000 V/cm.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a diagram exhibiting the principle of the present invention.

Figure 2 is a diagram exhibiting the principle of the present invention.

Figure 3 is a microscopic photograph exhibiting an embodiment of an example of the present invention.

Figure 4 is a microscopic photograph exhibiting another embodiment of an example of the present invention.

Figure 5 is a microscopic photograph exhibiting another embodiment of an example of the present invention.

Figure 6 is a microscopic photograph exhibiting another embodiment of an example of the present invention.

Figure 7 is a microscopic photograph exhibiting another embodiment of an example of the present invention.

Figure 8 is a microscopic photograph exhibiting another embodiment of an example of the present invention.

Figure 9 is a microscopic photograph exhibiting another embodiment of an example of the present invention.

Figure 10 is a microscopic photograph exhibiting an embodiment of another example of the present invention.

Figure 11 is a microscopic photograph exhibiting another embodiment of another example of the present invention.

Figure 12 is a microscopic photograph exhibiting an embodiment of another example of the present invention.

Figure 13 is a microscopic photograph exhibiting another embodiment of another example of the present invention.

Figure 14 is a microscopic photograph exhibiting an embodiment of another example of the present invention.

Figure 15 is a microscopic photograph exhibiting another embodiment of another example of the present invention.

Figure 16 is a diagram obtained by a measurement which exhibits the polarization energy in an example of the present invention.

Figure 17 is a diagram obtained by a measurement which exhibits the polarization energy in another example of the present invention.

Figure 18 is a diagram obtained by a measurement which exhibits the polarization energy in another example of the present invention.

The numbers in the above figures have the following meanings:

- 1: A ceramic treated by polarization (a space formed by removing the ceramic)
- 2: An N-surface
- 3: A newly formed bone
- 4: A P-surface

- 5: A cell similar to a connective tissue
- 6: An osteoblast
- 7: Medulla ossium
- 8: A barium titanate ceramic (a space formed by removing the ceramic)
- 9: A cortical bone
- 10: A productive cell
- 11: A liver cell
- 12: Cells arranged in order
- 13: Cells arranged in disorder
- 14: An O-surface

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention provides a method for controlling organisms which comprises growing, decreasing, activating or inactivating cells, bacteria, viruses or fungi at the N-surface or the P-surface of a ceramic which is formed by treating the ceramic by polarization, as described in Claim 1.

The present invention also provides the method for controlling organisms described in Claim 1, wherein the ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are materials selected from hydroxyapatite ceramics, barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially

stabilized zirconia ceramics; ion conductive alumina (so-called β -alumina) ceramics; and piezoelectric ceramics containing lead.

The present invention also provides the method for controlling organisms described in any of Claims 1 and 2, wherein the ceramic is powder, fiber or a coating film.

The present invention provides a material for controlling organisms which is a ceramic treated by polarization so that cells, bacteria, viruses or fungi are grown, decreased, activated or inactivated at the N-surface or the P-surfaces of the ceramic which is formed by the treatment, as described in Claim 4.

The present invention also provides the material for controlling organisms described in Claim 4, wherein the ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are materials selected from hydroxyapatite ceramics, barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially stabilized zirconia ceramics; ion conductive alumina (so-called β -alumina) ceramics; and piezoelectric ceramics containing lead.

The present invention also provides the material for controlling organisms described in any of Claims 4 and 5, wherein the ceramic is powder, fiber or a coating film.

At the N-surface of a ceramic treated by polarization, osteoblasts grow and ossification proceeds rapidly. Therefore, damages on a bone can be recovered rapidly when a material for filling bones or an artificial bone

is covered with powder of a ceramic treated by polarization or is coated with a film of a ceramic treated by polarization. When an implant material for orthopaedic surgery and dental treatments which is made of a metal such as titanium or a polymer and coated with a ceramic having affinity to biomaterials on the surface is used after the treatment by polarization, osteoblasts grow at the N-surface of the ceramic treated by polarization and ossification proceeds rapidly. Thus, the ability to recover is enhanced.

As described above, in the clinical application of the ceramic treated by polarization in accordance with the present invention, ossification proceeds at the N-surface in the early stage of about one week when the ceramic is used as an implant material of articulation coxa or an artificial radix dentis. This surgically very important property, which is called early fixing, is not found in conventional materials and has attracted attention. Moreover, the advantage of the material in accordance with the present invention is not limited to the above. In clinical applications for longer periods of several weeks to several months, or still longer, it is confirmed that ossification proceeds at the P-surface to about the same extent with that at the N-surface. Based on this knowledge, it is confirmed in the clinical application of the ceramic treated by polarization in accordance with the present invention that the ceramic can be used not only as the implant material but also in other applications such as retaining bones in osteoporosis.

Figure 1 is a diagram exhibiting the principle of the present invention. At the N-surface or the P-surface of the ceramic treated by polarization, cells of an organism are adsorbed together with inorganic

ions and proteins for ossification. These substances are embedded and stay there for a long time and form a new bone. The mechanism for the ossification has not been elucidated. The ossification may arise based on the property of genes, the properties of proteins at the surface of the cells or the properties of the inside of the cells or from other causes. The mechanism is under an intensive study.

In the inside of an organism, the N-surface or the P-surface of the ceramic treated by polarization can affect cells and tissues of organisms so that cells of the organisms, immunization cells and lymph corpuscles are grown, cell tissues and nerve cells are activated and various tissues and cells are regenerate and grown. Conventional cell incubators made of a polymer or glass have problems such as elution of the material of the incubators. When a material coated with the ceramic which has affinity to biomaterials and is treated by polarization is used as the material for an incubator, the obtained incubator exhibits a great effect of promoting growth of cells and tissues.

The N-surface or the P-surface of the ceramic treated by polarization affects bacteria or viruses so that bacteria or viruses are grown and activated. Therefore, a material for an incubator exhibiting a great effect of promoting growth of bacteria or viruses can be obtained.

On the other hand, bacteria, viruses or fungi may be decreased or inactivated on both or either one of the N-Surface and the P-surface of the ceramic treated by polarization. This behavior may be different depending on the type of microorganisms. Therefore, antimicrobial food wares and various types of antimicrobial instruments can be prepared by using the N-surface and the P-surface of the ceramic formed by the

treatment by polarization separately in various ways.

Figure 2 is a diagram exhibiting a model showing the antimicrobial effect. To the P-surface of the ceramic treated by polarization, bacteria are adsorbed together with chlorine ion and the bacteria are killed by the chlorine ion. Thus, the antimicrobial effect is exhibited.

The present invention provides the method for selective adsorption of proteins which comprises selectively adsorbing drugs, nutrients and proteins by utilizing difference in adsorption properties among the N-surface, the O-surface (a neutral surface placed between the N-surface and the P-surface) and the P-surface of a ceramic which are formed by treating the ceramic by polarization, as described in Claim 7.

The present invention also provides the material for selective adsorption of proteins which is a ceramic treated by polarization so that drugs, nutrients and proteins are selectively adsorbed due to difference in adsorption properties among the N-surface, the O-surface and the P-surface of the ceramic which are formed by treating the ceramic, as described in Claim 8.

The present invention also provides the material for selective adsorption for proteins described in Claim 8, wherein the ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are materials selected from hydroxyapatite ceramics, barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially stabilized zirconia ceramics; ion conductive alumina (so-

called β -alumina) ceramics; and piezoelectric ceramics containing lead.

As the surfaces of the ceramic treated by polarization, the N-surface, the P-surface and the O-surface having no polarity as the boundary between the N-surface and the P-surface are present. The selective adsorption of drugs, nutrients and proteins can be achieved by taking advantage of the difference in the adsorption properties among the N-surface, the O-surface and the P-surface. By soaking the ceramic into a solution or by placing the ceramic inside a tissue, various types of drugs, nutrients and proteins can be selectively adsorbed to the different surfaces in accordance with the types and are separated with respect to the types. The ceramic can also be used as a sensor which detects the presence of a specific drug or the like.

As described above, in accordance with the present invention, organisms such as cells, bacteria, viruses or fungi can be grown, decreased, activated or inactivated at the N-surface or the P-surface of the ceramic which is formed by the treatment by polarization. Moreover, the control of organisms can be conducted in a desired manner by suitably selecting the ceramic treated by polarization with respect to the amount of the stored polarization energy and the type of the ceramic.

In the present invention, controlling organisms means controlling, i.e., growing, decreasing, activating, inactivating or the like, organisms such as cells, bacteria, viruses, fungi and the like.

The present invention also provides a cement material for filling bones and dental applications which comprises powder or fiber of a ceramic treated by polarization, as described in Claim 11.

The powder of the ceramic treated by polarization exhibits great

chemical reactivity. Therefore, the above cement can be hardened more rapidly than conventional dental cements or orthopedic cements and exhibits a greater strength. By using the powder of the ceramic treated by polarization singly or as a mixture with conventional cement materials, an excellent cement material which is rapidly hardened and exhibits a great strength can be provided.

The present invention also provides the cement material described in Claim 11, which comprises needle-shaped powder or fiber of a ceramic treated by polarization.

The needle-shaped powder or fiber of the ceramic shows a greater degree of entanglement due to the elongated shape and provides a dental cement or an orthopedic cement exhibiting a greater reinforcing effect.

The needle-shaped powder and the fiber are formed on the surface of a metal such as titanium and aluminum on which scratches are formed in accordance with the biomimetic coating method. The mechanism of the formation of the needle-shaped powder or the fiber has not been elucidated. The unstable condition of the surface having scratches may lead to the formation of the needle-shaped materials rather than an appatite layer.

Examples of the method for coating a substrate with the ceramic include the biomimetic method, the plasma spray method, the sputtering method, the electrophoretic deposition followed by sintering, the dip-coating method and the functionally gradient composite coating method. In accordance with the biomimetic method, various substrates are coated with appatite coatings by utilizing the principle of formation of bones in organisms. Into a solution (a simulated body fluid) having pH of 7.25 and concentrations of ions adjusted to about the same values as those in the

human body fluid, a substrate and a glass containing calcium and silica as the main components are soaked for 1 to 4 days at 36.5°C. Silicate ion eluted from the glass is attached to the surface of the substrate and absorbs calcium ion and phosphate ion in the solution to form an appatite layer. The surfaces of metals, ceramics and macromolecular synthetic resins can be coated with appatite in accordance with this method.

The present invention also provides a cement material described in any of Claims 14 and 15, wherein the ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are materials selected from hydroxyappatite ceramics, barium titanate ceramics, strontium hydroxyappatite ceramics, hydroxyappatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially stabilized zirconia ceramics; ion conductive alumina (so-called β -alumina) ceramics; and piezoelectric ceramics containing lead.

The present invention also provides a biomaterial which is obtained by treating a ceramic having affinity to biomaterials by polarization in an atmosphere of steam at a temperature from a room temperature to 1,000°C at a voltage of 10 to 100,000 V/cm.

The ceramic can be treated by polarization at a temperature lower than the room temperature or at a voltage lower than 10 V/cm. However, it takes a long time for the polarization and the amount of the energy stored in the ceramic is small. The ceramic can be treated by polarization at a temperature higher than 1,000°C or a voltage higher than 100,000 V/cm. However, the energy is not stored in the ceramic but lost as the

current which flows out and the amount of the energy stored in the ceramic is smaller than the expected amount. Therefore, from the standpoint of the time for the treatment by polarization and the amount of the stored energy, it is preferable that the biomaterial is obtained by treatment by polarization in the condition of a temperature from a room temperature to 1,000°C and a voltage from 10 to 100,000 V/cm.

The optimum condition for the treatment by polarization is different depending on the type of the ceramic for the polarization and can be obtained by repeating ordinary experiments with respect to individual ceramics.

The present invention also provides the biomaterial described in any of Claims 14 and 15, wherein the ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are materials selected from hydroxyapatite ceramics, barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially stabilized zirconia ceramics; ion conductive alumina (so-called β -alumina) ceramics; and piezoelectric ceramics containing lead.

Strontium hydroxyapatite and hydroxyapatite ceramics containing calcium or strontium as solid solutions are successfully synthesized by sintering powder prepared in accordance with a wet synthesis process by heating in steam in a condition such that the lattice OH^- is not vaporized, for example at 1200°C for 1 to 5 hours.

The solid solution described above means a mixture obtained by

mixing components without destroying the structure or a mixture in the condition obtained by such mixing.

The advantages of the present invention are summarized in the following.

As will be specifically shown with reference to examples, at the N-surface of the ceramic treated by polarization in accordance with the present invention, osteoblast grows in the early stage of about one week and ossification proceeds rapidly. At the P-surface of the ceramic, ossification proceeds in a manner similar to that at the N-surface over a longer period of several weeks to several months. Therefore, by applying powder or fiber of the ceramic treated by polarization or a film coated with the ceramic treated by polarization to fillers for bones or artificial bones, recovery of the bones can be achieved rapidly and surely. This method can be applied to retaining bones in osteoporosis. By using an implant material for orthopaedic surgery and dental treatments in which the surface of a metal such as titanium or a polymer is coated with the ceramic having affinity to biomaterials after the treatment by polarization, osteoblast grows in the early stage of about one week and ossification proceeds rapidly at the N-surface or the P-surface of the ceramic treated by polarization and the ability of recovery increases.

The N-surface or the P-surface of the ceramic treated by polarization can affect cells and tissues of organisms so that cells of the organisms, immunization cells and lymph corpuscles are grown, cell tissues and nerve cells are activated and various tissues and cells are regenerated and grown.

Conventional cell incubators made of a polymer or glass have

problems such as elution of the material. When a material coated with the ceramic which has affinity to biomaterials and is treated by polarization is used as the material for an incubator, the obtained incubator exhibits a great effect of promoting growth of cells and tissues.

The N-surface or the P-surface of the ceramic treated by polarization affects bacteria or viruses so that bacteria or viruses are grown and activated. Therefore, a material for an incubator exhibiting a great effect of promoting growth of bacteria or viruses can be obtained.

On the other hand, bacteria, viruses or fungi may be decreased or inactivated on both or either one of the N-Surface and the P-surface of the ceramic treated by polarization. This behavior may be different depending on the type of microorganisms. Therefore, antimicrobial food wares and various types of antimicrobial instruments can be prepared by using the N-surface and the P-surface of the ceramic formed by the treatment by polarization separately in various ways.

As the surfaces of the ceramic treated by polarization, the N-surface, the P-surface and the O-surface having no polarity as the boundary between the N-surface and the P-surface are present. The selective adsorption of drugs, nutrients and proteins can be achieved by taking advantage of the difference in the adsorption properties among the N-surface, the O-surface and the P-surface. By soaking the ceramic into a solution or by placing the ceramic inside a tissue, various types of drugs, nutrients and proteins can be selectively adsorbed to the different surfaces in accordance with the types and are separated with respect to the types. The ceramic can also be used as a sensor which detects the presence of a specific drug or the like.

As described above, the method for controlling organisms which comprises growing, decreasing, activating or inactivating cells, bacteria, viruses or fungi at an N-surface or a P-surface of a ceramic which is formed by treating the ceramic by polarization and the material therefor are provided.

The powder of the ceramic treated by polarization exhibits great chemical reactivity. Therefore, the powder can be hardened more rapidly than conventional dental cements and orthopedic cements and exhibits a greater strength. By using the powder of the ceramic treated by polarization singly or as a mixture with conventional cement materials, an excellent cement material which is rapidly hardened and exhibits a great strength can be provided.

The needle-shaped powder or fiber of the ceramic shows a greater degree of entanglement due to the elongated shape and provides a dental cement or an orthopedic cement exhibiting a greater reinforcing effect.

The biomaterial advantageous from the standpoint of the time for the treatment by polarization and the amount of the stored energy can be obtained by treating a ceramic having affinity to biomaterials by polarization in an atmosphere of steam at a temperature from a room temperature to 1,000°C at a voltage from 10 to 100,000 V/cm.

EXAMPLES

The present invention will be described more specifically with reference to examples exhibited by figures in the following.

Figures 3 to 5 are photographs exhibiting the reaction of living tissues when a hydroxyapatite ($\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$) ceramic treated by

polarization is embedded inside medulla ossium of an adult beagle. Figure 3 is a photograph magnified 200 times. Newly formed bones 3 are found at the N-surface 2 of the hydroxyapatite and bleeding is found at the P-surface 4.

Figure 4 is a photograph exhibiting another P-surface 4 which is magnified 400 times. A newly formed bone 3 is found at a position separated from the P-surface. Cells 5 having a long cytoplasm which are similar to connective tissues are arranged in the vicinity of the P-surface.

Figure 5 is a photograph exhibiting another N-surface 2 which is magnified 400 times. A newly formed bone 3 is found at a position adjacent to the N-surface 2. The cell of a single layer adjacent to the N-surface 2 is considered to be an osteoblast 6. 7 shows medulla ossium and 1 shows the space formed by removing the ceramic.

Figure 6 is a photograph magnified 200 times which exhibits the reaction of living tissues when a barium titanate ceramic 8 is placed inside medulla ossium 6 of an adult beagle for 7 days. Newly formed bones 3 with protrusions are found along the N-surface 2. In contrast, almost no newly formed bones are found at the P-surface 4. 9 shows a cortical bone.

Figures 7 and 8 are photographs magnified 400 times which exhibits the reaction of living tissues when a barium titanate ceramic 8 treated by polarization is placed inside a living organ (liver of an adult beagle) for 7 days. In Figure 7, formation of productive cells 10 is found at the N-surface 2. In Figure 8, formation of cells similar to connecting tissues is found at the P-surface. 11 shows the liver tissue.

Figure 9 is a photograph magnified 200 times which exhibits the reaction of living tissues when barium titanate ceramic treated by

polarization 8 is placed inside a living organ (muscle of an adult beagle) for 7 days. At the N-surface 2, cells arranged in order 12 are formed. In contrast, cells arranged in disorder 13 are found at the P-surface.

Figure 10 shows phase-contrast microscopic photographs exhibiting behaviors of osteoblasts cultured for 73 hours in a glass cell culture dish coated with a hydroxyapatite ceramic which was not treated by polarization (the top photograph) and with a hydroxyapatite ceramic which was treated by polarization (the middle and bottom photographs). The coating was made in accordance with the sputtering method. In the top photograph exhibiting the cell culture dish which was not treated by polarization, the O-surface 14 is rough. In contrast, in the middle photograph exhibiting the cell culture dish which was treated by polarization, densely grown osteoblasts are found at the N-surface 2. At the P-surface 4 in the bottom photograph, the surface has cracks and almost no growth of osteoblasts can be found.

Figure 11 shows photographs exhibiting the conditions of the surfaces of a strontium hydroxide apatite ceramic treated by polarization after being soaked into blood serum for 5 days. The photographs at the top row, the middle row and the bottom row exhibit the O-surface, the P-surface and the N-surface, respectively. The photographs at the left column, the middle column and the right column exhibit photographs magnified 100 times, 200 times and 400 times, respectively. At the O-surfaces 14 shown at the top row which were not polarized, osteocytes and proteins are adsorbed in disorder. Proteins are adsorbed at the P-surfaces 4 shown at the middle row and osteocytes are adsorbed at the N-surfaces 2 shown at the bottom row. This result shows that, when an

implant material is coated with a layer of a ceramic treated by polarization which has suitable adsorption properties, drugs, nutrients and proteins are selectively adsorbed by utilizing the difference in the adsorption properties among the O-surface the P-surface and N-surface of the ceramic which are formed by treating the ceramic by polarization.

Figure 12 shows photographs exhibiting the conditions of the surfaces of a hydroxyapatite ceramic coating film formed on a titanium substrate in accordance with the sputtering method. The left end photograph exhibits the conditions before being soaked into a simulated body fluid. The photographs at the middle left, the middle right and the right end exhibit the conditions of the P-surface, the O-surface and the N-surface, respectively, after being soaked into a simulated body fluid for 1 day. At the P-surface, proteins and scattered portions like osteoblasts are found. At the N-surface, numerous tissues like osteoblasts are found and various tissues are found in disorder.

In the sputtering method, gas molecules are positively ionized by a high voltage in a vacuum, accelerated to a high speed and clashed against a cathode (a target) such as powder and ceramics of hydroxyapatite and calcium phosphate. Particles discharged from the target coat a substrate such as a titanium substrate disposed at a position faced to the target.

Figure 13 shows photographs exhibiting the conditions of the surfaces of a hydroxyapatite ceramic coating films formed on a titanium substrate in accordance with the biomimetic method. The left end photograph exhibits the conditions before being soaked into a simulated body fluid. The photographs at the middle left, the middle right and the right end exhibit the conditions of the P-surface, the O-surface and the N-

surface, respectively, after being soaked into a simulated body fluid for 1 day. At the P-surface, small portions like osteoblasts are found. At the N-surface, sufficiently grown up tissues like osteoblasts are found and tissues of intermediate sizes are found at the O-surface.

Figure 14 shows photographs exhibiting the conditions of the surfaces of a hydroxyapatite ceramic coating films formed on a titanium substrate in accordance with the plasma spray method. The left end photograph exhibits the conditions before being soaked into a simulated body fluid. The photographs at the middle left, the middle right and the right end exhibit the conditions of the P-surface, the O-surface and the N-surface, respectively, after being soaked into a simulated body fluid for 1 day. At the P-surface and the O-surface, only small portions like cells are found. At the N-surface, sufficiently grown up tissues like osteoblasts are found.

In the plasma spray method, a ceramic in the condition of melting or close to melting is blown toward a substrate at a high speed to form a coating layer using an arc discharge as the means of melting and blowing. When a gas at a low temperature is introduced into the periphery of a plasma, the temperature of the central portion of the plasma jet reaches several ten thousands degrees centigrade. When powder of a hydroxyapatite having a particle diameter of several to several tens micrometers is introduced at a speed of several hundreds meters per second with a carrier gas, the object exposed to the stream is rapidly cooled at a rate of 10^4 to 10^6 °C/second and a film of a hydroxyapatite ceramic in the form of a lamella is formed at the substrate.

Figure 15 shows photographs exhibiting the conditions of the

surfaces of a needle-shaped hydroxyapatite ceramic coating film formed on a titanium substrate in accordance with the metal chelate dissociation method. The left end photograph exhibits the conditions before being soaked into a simulated body fluid. The photographs at the middle left, the middle right and the right end exhibit the conditions of the P-surface, the O-surface and the N-surface, respectively, after being soaked into a simulated body fluid for 2 days. At the P-surface and the O-surface, only small portions like cells which barely form needle shapes are found. At the N-surface, sufficiently grown up tissues like osteoblasts are found.

Figures 12 to 15 show the examples exhibiting that, when hydroxyapatite coating films are formed in accordance with various conventional coating methods showing affinity to biomaterials, the effect of the treatment by polarization can be obtained independently of the coating method adopted.

It has been confirmed by the present inventors that the effect of the treatment by polarization similar to that obtained by using the hydroxyapatite ceramics can be exhibited by using various glasses and crystallized glasses including barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate and various other materials including stabilized and partially stabilized zirconia ceramics, ion conductive alumina (so-called β -alumina) ceramics and piezoelectric ceramics containing lead.

Figures 16 to 18 are diagrams exhibiting the polarization energy stored in the hydroxyapatite ceramics treated by polarization. The

energy (the polarization energy) stored by the polarization in the polarized ceramic is detected by measuring the heat-stimulated electric current which is generated by discharging the energy stored in the polarized ceramics by heating.

Figure 16 shows a diagram exhibiting the polarization energy stored in a hydroxyapatite ceramic treated by polarization in the condition of 300°C, 2,000 V/cm and 1 hour in the atmosphere of steam. The peak value of the heat-stimulated electric current generated from the stored energy is about 5,000 pA (pico ampere).

Figure 17 shows a diagram exhibiting the polarization energy stored in a hydroxyapatite ceramic treated by polarization in the condition of 350°C, 2,000 V/cm and 1 hour in the atmosphere of steam. The peak value of the heat-stimulated electric current generated from the stored energy is about 5,200 pA (pico ampere).

Figure 18 shows a diagram exhibiting the polarization energy stored in a hydroxyapatite ceramic treated by polarization in the condition of 400°C, 2,000 V/cm and 1 hour in the atmosphere of steam. The peak value of the heat-stimulated electric current generated from the stored energy is greater than about 19,000 pA (pico ampere).

The optimum condition for the treatment by polarization is different depending on the type of the ceramic for the polarization and can be obtained in accordance with ordinary experimental methods. By comparing the diagram shown in Figure 18 with the diagrams shown in Figures 16 and 17, the optimum condition for the treatment by polarization of the hydroxyapatite ceramic is obtained as: 400°C, 1,000 V/cm and 1 hour in the atmosphere of steam.

WHAT IS CLAIMED IS:

1. A method for controlling organisms which comprises growing, decreasing, activating or inactivating cells, bacteria, viruses or fungi at an N-surface or a P-surface of a ceramic which is formed by treating the ceramic by polarization.
2. A method for controlling organisms according to Claim 1, wherein the ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are materials selected from hydroxyapatite ceramics, barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially stabilized zirconia ceramics; ion conductive alumina (so-called β -alumina) ceramics; and piezoelectric ceramics containing lead.
3. A method for controlling organisms according to any of Claims 1 and 2, wherein the ceramic is powder, fiber or a coating film.
4. A material for controlling organisms which is a ceramic treated by polarization so that cells, bacteria, viruses or fungi are grown, decreased, activated or inactivated at an N-surface or a P-surfaces of the ceramic which is formed by the treatment.
5. A material for controlling organisms according to Claim 4, wherein the

ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are materials selected from hydroxyapatite ceramics, barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially stabilized zirconia ceramics; ion conductive alumina (so-called β -alumina) ceramics; and piezoelectric ceramics containing lead.

6. A material for controlling organisms according to any of Claims 4 and 5, wherein the ceramic is powder, fiber or a coating film.

7. A method for selective adsorption of proteins which comprises selectively adsorbing drugs, nutrients and proteins by utilizing difference in adsorption properties among an N-surface, an O-surface and a P-surface of a ceramic which are formed by treating the ceramic by polarization.

8. A material for selective adsorption of proteins which is a ceramic treated by polarization so that drugs, nutrients and proteins are selectively adsorbed due to difference in adsorption properties among an N-surface, an O-surface and a P-surface of a ceramic which are formed by treating the ceramic.

9. A material for selective adsorption of proteins according to Claim 8, wherein the ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are

materials selected from hydroxyapatite ceramics, barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially stabilized zirconia ceramics; ion conductive alumina (so-called β -alumina) ceramics; and piezoelectric ceramics containing lead.

10. A material for controlling organisms according to any of Claims 8 and 9, wherein the ceramic is powder, fiber or a coating film.

11. A cement material for filling bones and dental applications which comprises powder or fiber of a ceramic treated by polarization.

12. A cement material according to Claim 11, which is needle-shaped powder or fiber.


13. A cement material according to any of Claims 11 and 12, wherein the ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are materials selected from hydroxyapatite ceramics, barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially stabilized zirconia ceramics; ion conductive alumina (so-called β -alumina) ceramics; and piezoelectric ceramics containing lead.

14. A biomaterial which is obtained by treating a ceramic having affinity to biomaterials by polarization in an atmosphere of steam at a temperature from a room temperature to 1,000°C.


15. A biomaterial which is obtained by treating a ceramic having affinity to biomaterials by polarization at a voltage from 10 to 100,000 V/cm.

16. A biomaterial according to any of Claims 14 and 15, wherein the ceramic is a material or a combination of materials selected from the group consisting of glasses and crystallized glasses which are materials selected from hydroxyapatite ceramics, barium titanate ceramics, strontium hydroxyapatite ceramics, hydroxyapatite ceramics containing calcium or strontium as solid solutions, lithium niobate ceramics, sodium niobate ceramics, potassium niobate ceramics and calcium phosphate; stabilized and partially stabilized zirconia ceramics; ion conductive alumina (so-called β -alumina) ceramics; and piezoelectric ceramics containing lead.


(1) At the initial time



(2) At an intermediate time





(3) After use for a long time




Formation of a new bone

(1) At the initial time




● Chlorine ion
 Bacterium

(2) At an intermediate time





(3) After use




Bacteria killed


【图 8】







【图5】






【图 8】






14

Control (Cell culture dish)



2

Negatively charged surface





4


Positively charged surface

0053150-022200








【図 14】




【図 15】









DECLARATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor, if only one name is listed below, or an original, first and joint inventor, if plural names are listed below, of the subject matter which is claimed and for which a patent is sought on the invention entitled **METHOD FOR CONTROLLING ORGANISMS AND MATERIAL THEREFOR, METHOD FOR SELECTIVE ADSORPTION OF PROTEINS AND MATERIAL THEREFOR, CEMENT MATERIAL AND BIOMATERIAL**, the specification of which is attached hereto.

I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose to the United States Patent and Trademark Office (the Office), all information which is known by me to be material to patentability as defined in Title 37, Code of Federal Regulations (C.F.R.), Section 1.56.

CLAIM OF PRIORITY

I hereby claim foreign benefits under Title 35, United States Code (U.S.C.), Section 119(a)-(d) or § 365(b), of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below any foreign application for patent or inventor's certificate, or of any PCT international application, having a filing date before that of the application on which priority is claimed.

Patent Application No. 11-77089 filed in Japan on March 23, 1999

Patent Application No. 2000-3545 filed in Japan on January 12, 2000

I hereby claim the benefit under 35 U.S.C. § 120, of any United States application(s), or § 365(c) of any PCT international application designating the United States of America, listed below and, insofar as the above-identified specification, including claims, discloses and claims subject matter in addition to that disclosed in the prior pending application(s), listed below, I acknowledge the duty to disclose to the Office, all information which is known by me to be material to patentability as defined in 37 C.F.R. § 1.56, which became available between the filing date of the prior application and the national or PCT international filing date of this application.

U.S. Serial No. {serial no.}, filed on {date}, and now {status}

POWER OF ATTORNEY

I hereby appoint the practitioners associated with the Customer Number provided below (*i.e.*, the practitioners associated with the law firm of Price, Henefeld, Cooper, DeWitt and Litton) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith. Please direct all correspondence to the address associated with that Customer Number.

Customer Number 000,277

All statements made herein of my own knowledge are true and all statements made on information and belief are believed to be true, and further, these statements are made with the knowledge that willful false statements and the like are punishable by fine or imprisonment, or both, under 18 U.S.C. § 1001, and that such willful false statements may jeopardize the validity of this application or any patent issued thereon.

Sole or First joint inventor:

Kimihiro Yamashita	Date
Citizenship: Japan	
Residence: 4-36-20 Shimotakaido	
Suginami-ku, Tokyo-to, Japan	
Post Office Address: 4-36-20 Shimotakaido	
Suginami-ku, Tokyo-to, Japan	

Applicant(s) or Patentee(s) : Kimihiro Yamashita
Serial or Patent No. :
Filed or Issued :
For : METHOD FOR CONTROLLING ORGANISMS AND MATERIAL THEREFOR,
METHOD FOR SELECTIVE ADSORPTION OF PROTEINS AND MATERIAL
THEREFOR, CEMENT MATERIAL AND BIOMATERIAL

**VERIFIED STATEMENT (DECLARATION) CLAIMING SMALL ENTITY
STATUS (37 CFR §1.9(f) and 1.27(c)) - SMALL BUSINESS CONCERN**

I hereby declare that I am:

- ☐ the owner of the small business concern identified below:
☒ an official of the small business concern empowered to act on behalf of the concern identified below.

NAME OF CONCERN: Yuugen Gaisha Neichamateriaru
ADDRESS OF CONCERN: Otsu 444-1 Johenmachi, Minamiuwa-gun, Ehime-ken, Japan

I hereby declare that the above identified small business concern qualifies as a small business concern as defined in 13 CFR §121.3-18, and reproduced in 37 CFR §1.9(d), for purposes of paying reduced fees under sections 41(a) and (b) of Title 35, United States Code, in that the number of employees of the concern, including those of its affiliates, does not exceed 500 persons. For purposes of this statement, (1) the number of employees of the business concern is the average over the previous fiscal year of the concern of the persons employed on a full-time, part-time or temporary basis during each of the pay periods of the fiscal year, and (2) concerns are affiliates of each other when either, directly or indirectly, one concern controls or has the power to control the other, or a third party or parties controls or has the power to control both.

I hereby declare that rights under contract or law have been conveyed to and remain with the small business concern identified above with regard to the invention, entitled: METHOD FOR CONTROLLING ORGANISMS AND MATERIAL THEREFOR, METHOD FOR SELECTIVE ADSORPTION OF PROTEINS AND MATERIAL THEREFOR, CEMENT MATERIAL AND BIOMATERIAL by inventor Kimihiro Yamashita described in:

- ☒ the specification filed herewith.
☐ application Serial No. _____, filed _____.
☐ Patent No. _____, issued _____.

If the rights held by the above identified small business concern are not exclusive, each individual, concern or organization having rights to the invention is listed below* and no rights to the invention are held by any person, other than the inventor, who could not qualify as an independent inventor under 37 CFR §1.9(c) or by any concern which would not qualify as a small business concern under 37 CFR §1.9(d) or a nonprofit organization under 37 CFR §1.9(e). *NOTE: Separate Verified Statements are required from each named person, concern or organization having rights to the invention averring to their status as small entities (37 CFR §1.27).

NAME _____
ADDRESS _____
☐ INDIVIDUAL ☐ SMALL BUSINESS CONCERN ☐ NON-PROFIT ORGANIZATION

I acknowledge the duty to file, in this application or patent, notification of any change in status resulting in loss of entitlement to small entity status prior to paying, or at the time of paying, the earliest of the issue fee or any maintenance fee due after the date on which status as a small entity is no longer appropriate. (37 CFR §1.28(b)).

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application, any patent issuing thereon, or any patent to which this Verified Statement is directed.

NAME OF PERSON SIGNING Soichiro Tsuzuki
TITLE OF PERSON OTHER THAN OWNER President
ADDRESS OF PERSON SIGNING _____

SIGNATURE _____ DATE _____